

Chipboard

Technical Data



KC/QUAL/DOC/0015 - 14/12/10

KRONOSPAN P1 SPECIFIC PROPERTIES:

PROPERTY	TEST METHOD	UNIT	EN SPECIFICATION (EN 312) - 18MM	KRONOSPAN VALUES (18MM)
Internal Bond	EN 319	N/mm ²	0.24	0.35
Bending Strength	EN 310	N/mm ²	11.5	11.5
MOE	EN 310	N/mm ²	N/A	2100

KRONOSPAN P2 SPECIFIC PROPERTIES:

PROPERTY	TEST METHOD	UNIT	EN SPECIFICATION (EN 312) - 18MM	KRONOSPAN VALUES (18MM)
Internal Bond	EN 319	N/mm ²	0.35	0.45
Surface Soundness	EN 311	N/mm ²	0.8	0.8
Bending Strength	EN 310	N/mm ²	13	13
MOE	EN 310	N/mm ²	1600	1800
Target Density	EN 323	KG/M ³	N/A	650



The mark of responsible forestry

