

# TECHNICAL DATA SHEET

## EUROSPAN® JP F0.3 (F\*\*\*\*) P2

Recipe: 118

Application: Base particle board for interior fitments (including furniture) for use in dry conditions with reduced formaldehyde release according to Japanese standard JIS A 5908:2003.

Plant: Radauti , St. Johann



### Board type in line with EN 312-2

Mechanical properties Board mean values	Unit	Board thickness		
	[mm]	>6-13	>13-20	>20-25
Density	[kg/m³]	Plant specific		
Internal Bond strength EN 319	[N/mm²]	0.4	0.35	0.30
Bending strength EN 310	[N/mm²]	11	11	10,5
Modulus of elasticity EN 310	[N/mm²]	1800	1600	1500
Surface soundness EN 311	[N/mm²]	0.8		
Moisture content *1 EN 322	[%]	5-7		
Formaldehyde content *2	[class]	F****		

General Tolerances	Unit	Board thickness		
	[mm]	6-13	>13-20	>20-25
Length and width tolerance EN 324	[mm]	±5.0		
Squareness EN 324	[mm/m]	≤2.0		
Edge straightness tolerance EN 324	[mm/m]	≤1.5		
Thickness tolerance EN 324 (Sanded boards)	[mm]	±0.3		
Tolerance on the mean density within a board EN 323	[%]	±10		

Building physical properties	Unit	Board thickness		
	[mm]	6-13	>13-20	>20-25
<b>Fire behaviour category</b>				
Board thickness ≥ 9 mm and density ≥ 600 kg/m <sup>3</sup> in line with EN13986		D-s2, d0		
Board thickness < 9 mm in line with EN 13986		E		
<b>Water vapour diffusion resistance value</b>				
		μ moist	μ dry	
Mean density 600 kg/m <sup>3</sup>		15	50	
Mean density 900 kg/m <sup>3</sup>		20	50	
<b>Thermal conductivity EN 13986</b>				
Mean density 600 kg/m <sup>3</sup>	W/(m*K)	0.12		
Mean density 900 kg/m <sup>3</sup>		0.18		
<b>Air sound insulation EN 13986</b>				
EN 13986		$R = 13 \times \lg(m_A) + 14$ (m <sub>A</sub> = board surface weight kg/m <sup>2</sup> )		
<b>Sound absorption EN 13986</b>				
Frequency range		0.10		
250 Hz to 500 Hz		0.25		
1000 Hz to 2000 Hz				
<b>Biological durability EN 13986</b>				
EN 335-3		Hazard category 1 (no earth contact , dry 20%/65% relative humidity)		
<b>PCP content EN 13986</b>				
EN 13986	[ppm]	< 5		

\*1 On delivery

\*2 Formaldehyde content:

EGGER particleboard EUROSPAN® JP F 0.3 (F\*\*\*\*) achieves the formaldehyde class F\*\*\*\* according to the Japanese standard JIS A 5908:2003. The limit value is 0,3 mg/L according to Japanese test method JIS A 1460 (Desiccator). Additionally EGGER particleboard EUROSPAN® JP F 0.3 (F\*\*\*\*) reaches limit value 3.0 mg/100 over-dry board at moisture content of 6.5 %, according to the European test Method EN 120 (Perforator).

**Provisional note:**

This technical data sheet has been carefully drawn up to the best of our knowledge. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies. The contents of this technical leaflet should therefore not be considered as instructions for use or as legally binding.